

CARMYDUR, DESMODUR RC HARDENER FOR ADHESIVES



DESCRIPTION

Isocyanate hardener for various adhesives based on synthetic Rubber, or Polyurethane.

CHARACTERISTICS & USES

CARMYDUR is added in the above mentioned adhesive for making the bond stronger and increase also the heat and solvent resistance of the bond.

DIRECTIONS FOR USE

Add 3-5% hardener in the adhesive. Mix the two components thoroughly. Use the mixture in 1 - 2 hours for synthetic rubber (Neoprene), or in 6 hours for Polyurethane.

STORAGE

CARMYDUR can be stored for at least 12 months at a temperature of 20°C in well closed bottles.

TECHNICAL CHARACTERISTICS	UNITS	STANDARD	VALUE
Colour - Appearance			Light yellowish liquid
Density	(gr/ml)		1,015
Total Solid Content	(%)		35 ± 1
N C O Content	(%)		7 ± 0,2

Note: The measurements were taken in laboratory environment under a temperature of +23°C, Relative humidity 50 % and without ventilation. It is possible for them to vary depending on the conditions prevailing at the worksite, such as temperature, humidity, ventilation, absorbability of the substrate.

The technical information and instructions contained in the present brochure and referring to the application and end use of Thrakon products are based on the up to now know-how and experience of the Company with regards to the products and are provided in good faith as long as such products are stored, used and applied as per Thrakon recommendations. Due to the inability, on our part, to directly inspect the conditions prevailing at the worksite as well as the application procedures of the product, the Company does not provide any guarantee with regards to the adequacy of its products for specific purpose while the Company shall not bear any legal responsibility based on the information stated in the present brochure or any other written, oral, or otherwise provided recommendations and instructions. The users of the products are advised to perform a limited surface testing of the products adequacy for the eventual application and use intentions. Thrakon reserves the right to modify the features of its products without prior notification. All orders shall be approved only following acceptance of the above and under the eventual Commercial Policy terms of the Company. The issuance of the present brochure voids any prior version.