## **CARMYFIX CM – 35** HIGHT HEAT RESISTANCE NEOPRENE ADHESIVE



## DESCRIPTION

Low viscosity solvent soluble adhesive based on synthetic rubber and resins.

## **CHARACTERISTICS & USES**

**CARMYFIX CM - 35** is suitable for automatic application machines and widely used in shoe and leather manufacturing. It is recommended for strong adhesion on leather, sue for rubber, microcellular rubber etc. It provides strong, excellent primary bond and heat resistance with short drying time. Open tack time is also short and maximum 45

## **DIRECTIONS FOR USE**

**STORAGE** 

Clean thoroughly and roughen (if possible) both surfaces. Spread evenly the adhesive on both surfaces. Bond by pressing the surfaces after 20-25 minutes. Maximum bonding is achieved after 48 hours. Mixing at the material is advisable before each use. **CARMYFIX CM - 35** can be stored for at least 12 months at a temperature of 20°C in well closed cans.

TECHNICAL CHARACTERISTICS	UNITS	STANDARD	VALUE
Colour - Appearance			Light white - yellowish liquid
Viscosity	(cps)	Brookfield Viscometer RVT (10 rpm - spindle 2 - 20°C)	$3000 \pm 500$
Density	(gr/ml)	(20°C)	$0,88 \pm 0,03$
Total Solid Content	(%)		$22 \pm 1$
Open Tack Time	(min)		15 - 45
Drying Time	(min)		10 - 15

Note: The measurements were taken in laboratory environment under a temperature of +23<sup>u</sup>C, Relative humidity 50 % and without ventilation. It is possible for them to vary depending on the conditions prevailing at the worksite, such as temperature, humidity, ventilation, absorbability of the substrate.

The technical information and instructions contained in the present brochure and referring to the application and end use of Thrakon products are based on the up to now knowhow and experience of the Company with regards to the products and are provided in good faith as long as such products are stored, used and applied as per Thrakon recommendations. Due to the inability, on our part, to directly inspect the conditions prevailing at the worksite as well as the application procedures of the product, the Company does not provide any guarantee with regards to the adequacy of its products for specific purpose while the Company shall not bear any legal responsibility based on the information stated in the present brochure or any other written, oral, or otherwise provided recommendations and instructions. The users of the products are advised to perform a limited surface testing of the products adequacy for the eventual application and use intentions. Thrakon reserves the right to modify the features of its products without prior notification. All orders shall be approved only following acceptance of the above and under the eventual Commercial Policy terms of the Company. The issuance of the present brochure voids any prior version.